

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 4/40	A1	(11) International Publication Number: WO 00/22003 (43) International Publication Date: 20 April 2000 (20.04.00)
(21) International Application Number: PCT/EP99/07769 (22) International Filing Date: 11 October 1999 (11.10.99) (30) Priority Data: 98203407.6 12 October 1998 (12.10.98) EP (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): VAN SWIETEN, Andreas, Petrus [NL/NL]; Reinaldstraat 6, NL-6883 HM Velp (NL). WAANDERS, Petrus, Paulus [NL/NL]; Bëntinckstraat 13, NL-7471 SL Goor (NL). MALTHA, Annemarieke [NL/NL]; De Meren 1729, NL-6605 XS Wijchen (NL). (74) Agent: ARNOLD & SIEDSMA; Sweelinckplein 1, NL-2517 GK 's Gravenhage (NL).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>

(54) Title: REDOX POLYMERIZATION PROCESS

(57) Abstract

A process for emulsion polymerization comprising the steps of reacting together a polymerization initiator, a reductor, and a polymerizable species, with the proviso that the polymerization initiator is not a hydroperoxide, characterized in that the polymerization initiator and the reductor are reacted together to provide a free radical moiety of the initiator, whereupon this free radical moiety initiates polymerization of the polymerizable species, this step being carried out at an initial cold start temperature, whereafter the temperature is increased to follow a temperature profile to a final preselected polymerization temperature.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

REDOX POLYMERIZATION PROCESS

The present invention relates to a process for emulsion polymerization, to the polymers obtainable by such a process, and to their uses.

5

The production of water based resins, for example by means of emulsion polymerization techniques, is carried out thermally with inorganic persulfates. A problem with thermal polymerization is the process time, which leads to a less than desirable reactor output.

10

An object of the present invention is to provide an alternative polymerization process which aims to improve the process time.

The first aspect of the present invention provides a process according to claim 1.

15

Since the polymerization process according to the present invention provides a free radical initiator moiety by means of a redox reaction instead of by thermal decomposition, the polymerization can be carried out with a so-called "cold start", which involves the process time being reduced and the reactor output per unit time being increased.

20

A redox polymerization is known for tertiary butyl hydroperoxide "Trigonox A-W70". The inventors have shown, however, that a redox polymerization utilizing other organic peroxides provides unexpectedly good results.

25

The inventors have shown that polymerization can start at a lower initial temperature, which means that because of the longer "heating-up" time necessary in thermal polymerization, the polymerization time can be reduced utilizing the process of the current invention.

30

The inventors have furthermore demonstrated that the process according to the present invention enables a polymer with a very low residual monomer level to be

obtained, whilst, with respect to thermal polymerization, the amount of initiator used can be reduced.

Good results have been achieved under the conditions as defined in claims 2-6.

5

The polymerization initiator is most preferably a substantially non-water-soluble initiator, such as defined in claim 7 or 8, since these non-water-soluble initiators yield an unexpectedly high efficiency in polymerization.

10 This higher efficiency results in shorter polymerization times and in polymer resins with improved properties. The higher efficiency of the organic peroxides is expressed by the low level of residual monomers and by the low molecular weights (Mw/Mn) of the polymers formed.

15 Furthermore, the conductivity of the resins initiated with the organic peroxide/redox system is lower than for corresponding resins that were initiated by persulfates.

The reductor of the redox system preferably is chosen from the following group:
20 sodium formaldehyde sulfoxylate (SFS), sodium bisulfite, Ascorbic acid (vitamin C), aldehydes, for example glutaraldehyde, sodium metabisulfite, sodium dithionate, and sugars, wherein the reductor most preferably is sodium formaldehyde sulfoxide.

25 The polymerizable species preferably is chosen from the following group: acrylonitrile, acrylic acid, methyl acrylate, ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, methoxyethyl acrylate, dimethyl aminoacrylate, methacrylic acid, methyl methacrylate, ethyl methacrylate, butyl methacrylate, isobutyl methacrylate, 2-ethylhexyl methacrylate, lauryl methacrylate, stearic
30 methacrylate, dimethyl aminomethacrylate, allyl methacrylate, 2-hydroxyethyl

acrylate, 2-hydroxypropyl acrylate, 2-hydroxyethyl methacrylate, 2-hydroxypropyl methacrylate, acrylamide, methacrylamide, glycidyl acrylate, vinyl ester of versatic acid, styrene, para-methyl styrene, vinyl acetate, alpha-methyl styrene, wherein the polymerizable species most preferably comprises vinyl acetate
5 and/or the vinyl ester of versatic acid.

Further preferred process conditions are detailed in claims 11-15.

The polymerization is carried out in a conventional emulsion, for example in a
10 mixture of anionic and non-ionic surfactants such as Witconate (sodium alpha-olefin sulfonate) and Syntopon (ethoxylated nonylphenol); however, other emulsifiers or mixtures are also possible.

This emulsifier solution preferably is a mixture of nonionic and anionic emulsifiers
15 and most preferably is selected from the group consisting essentially of:

- long-chain aliphatic carboxylates (ionic)
- alkylbenzene sulfonates (ionic)
- alkyl sulphates (ionic)
- dialkylsulphosuccinate (ionic)
- 20 - ethoxylated alcohols (nonionic)
- ethoxylated alkyl phenols (nonionic)
- ethoxylated amine or amides (nonionic).

A second aspect of the present invention provides a polymer obtainable
25 according to this process.

The invention will now be further elucidated by way of the following examples. Examples 1-6 are comparative examples and Examples 7-12 are examples according to the present invention using a redox system. Examples 3, 4, 6, 8-12
30 were subjected to a temperature profile increasing from an initial temperature to a

final temperature, i.e. subjected to a so-called "cold-start", and Example 7 was carried out at constant temperature.

Procedure of preparation

- 5 The polymerization in all the examples was carried out in a 0.25 L glass reactor with a stirrer under nitrogen. A seed was prepared first by adding 10% of the reactive components at polymerization temperature.

The preparation of the seed was carried out as follows:

- 10 The reactor was filled with buffered (NaAc/HAc) emulsifier solution (Witconate/Syntopon), prepared with oxygen-free deionized water. At the polymerization temperature 10% of the pre-emulsion containing soaps (Witconate and Syntopon), monomers, and, in the case of the redox system according to the present invention, also reductor and catalyst, were added. In addition the solution
15 or pre-emulsion of the initiator was added to achieve control over the accurate dosing of the initiator.

- After a polymerization time of 30 minutes the remaining monomers, pre-emulsion, and initiator solution were dosed in 2.5 hours. In Examples 3, 4, 6, 8-12 the
20 temperature was increased to the final temperature in the same period, following a temperature profile. The final temperature was maintained for 1 hour.

The composition of the buffered soap solution used was as follows:

NaAC.3aq	0.25 g (sodium acetate)
25 HAc	0.11 g (acetic acid)
H ₂ O	30.3 g
Witconate	0.38 g (soap)
Syntopon	0.38 g (soap)

Example 1

Thermal system

The temperature was kept at 70°C during the polymerization. The composition of the used pre-emulsion was:

Witconate	1.28 g
Syntopon	1.28 g
H ₂ O	34.43 g
Vac (vinyl acetate)	52.5 g (monomer)
VEOVA (vinyl ester of versatic acid)	22.5 g (monomer)

5

The initiator solution was composed of 4.18 mmoles ammonium/sodium or potassium persulfate in 25 g H₂O. The total process time including the time needed for heating up the reactor contents to 70°C before polymerization amounted to 5.5 hours.

10

Examples 2, 5, 7

The temperature was kept at 70°C (Examples 2, 5) and 20°C (Example 7), respectively. The composition of the used pre-emulsions was as follows:

Witconate	1.28 g
Syntopon	1.28 g
H ₂ O	34.43 g
Peroxide	1.04-4.18 mmoles as mentioned in the examples
Vac (vinyl acetate)	52.5 g (monomer)
VEOVA (vinyl ester of versatic acid)	22.5 g (monomer)

- 15 The reductor SFS (sodium formaldehyde sulfoxide: 0.65 g) and the catalyst (FeSO₄ 16.7 mg) were dissolved in 25 g H₂O.
The total process time was 4 hours.

Examples 3, 4, 6, 8-12

The polymerization temperature was kept at 20°C for the first 30 minutes to prepare a seed. The temperature was then increased by 20°C/hour to 70°C following a temperature profile.

5

It is noted that other starting temperatures and temperature programmes can be used, either for initiating polymerization or for initiating and completing polymerization.

10 In all the examples the residual monomers were determined by gas chromatography (GC). The molecular weight of the prepared polymers was determined by gel permeation chromatography (GPC) with polystyrene for calibration. The conversion/solids content was determined by standard procedure. The viscosity was determined using a Brookfield digital viscometer.

15

The results are shown in Table 1.

Examples 13-2420 Procedure of preparation

The polymerization in all examples was carried out in a 0.25 L glass reactor with a stirrer under nitrogen. A seed was prepared first by adding 10% of the reactive components at polymerization temperature.

25 The preparation of the seed was carried out as follows:

The reactor was filled with the emulsifier solution (sodium lauryl sulfate in water) prepared with oxygen-free deionized water. At the starting polymerization temperature 10% of the pre-emulsion containing soap, monomers, and in the case of the redox system, also reductor and catalyst, were added. In addition the
30 solution or pre-emulsion of the initiator was added to achieve control over the

accurate dosing of the initiator.

After a polymerization time of 30 minutes the remaining monomers, pre-emulsion, and initiator solution were dosed in 2.5 hours. The temperature was increased to
5 the final temperature in the same period, following a temperature profile. The final temperature was maintained for 1 hour.

The composition of the soap solution was as follows:

- 0.10 g sodium lauryl sulfate (emulsifier)
- 10 25.0 ml deionized water

Pre-emulsion:

- 1.60 g sodium lauryl sulfate
- 30 ml deionized water
- 15 70 g monomer mixture (butylacrylate / styrene / methacrylic acid = 6/4/0.1)
including the initiator (1.04 meq), if not water-soluble.

The reductor SFS (sodium formaldehyde sulfoxylate 0.16 g) and the catalyst ($\text{Fe}^{2+}\text{SO}_4$ 2.8 mg) were dissolved in 10 ml water.

- 20 The molar ratio oxidator: reductor: Fe = 1: 1: 0.01

The results are shown in Tables 2 and 3.

Table 1

Example	Initiator	meq oxid.	conditions	residual Vac%	residual Veova %	Mw/Mn x1000	γ mS/cm	PS (nm)
1	K2S208	4.2	70°C thermal	0.10	0.074	630/50	5.3	180
2	K2S208	4.2	70°C redox	0.51	0.23	410/37	9.8	212
3	K2S208	4.2	20 → 70°C redox	0.27	0.095	790/64	10.3	197
4	K2S208	2.1	20° → 70°C redox	0.36	0.12	740/49	5.6	128
5	Tx A-W70 (tert-Butyl hydroperoxide)	4.2	70°C redox	0.096	0.30	290/19	3.4	189
6	Tx A-W70 (tert-Butyl hydroperoxide)	4.2	20 → 70°C redox	0.073	0.028	670/44	3.6	141
7	Tx 21 (tert-Butyl peroxy-2- ethylhexanoate)	4.2	20°C redox	0.054	0.067	170/18	3.1	143
8	Tx C (tert-Butyl peroxybenzoate)	4.2	20 → 70°C redox	0.17	0.11	150/22	3.2	175
9	Tx C (tert-Butyl peroxybenzoate)	2.1	20° → 70°C redox	0.049	0.03	270/35	2.2	190
10	Tx C (tert-Butyl peroxybenzoate)	1.5	20° → 70°C redox	0.082	0.022	560/48	1.9	181
11	Tx C (tert-Butyl peroxybenzoate)	1.05	20° → 70°C redox	0.048	<0.004	1000/48	1.7	148
12	Tx C (tert-Butyl peroxybenzoate) Without Fe2+	4.2	20 → 70°C redox	<0.016	0.009	770/106	3.1	172

Table 2 Emulsion:
 Theoretical solids content: VeoVa10/VAc-emulsions: 44%
 Reductant: SFS/Fe(II) Ox : SFS : Fe = 1 : 1 : 0.01

Initiator	Monomers	[Initiator] meq	Solids	Residual monomers VeoVa	Vac	Mw	Mn	D	pH
K ₂ S ₂ O ₈	VeoVa/VAc	1.4	39.8	0.65	1.23	482900	51900	9.30	2.30
	VeoVa/VAc	2.1	43.2	0.34	0.13	412000	59000	6.9	2.30
Tx C	VeoVa/VAc	1.4	42.2	n.d.	0.64	211300	33300	6.34	4.35
	VeoVa/VAc	2.8	40.5	0.97	0.26	695000	99600	6.98	3.61
Tx 117	VeoVa/VAc	1.4	42.5	n.d.	n.d.	278200	31400	8.85	4.55
Laurox	VeoVa/VAc	1.4	16.5	n.d.	n.d.	728500	141500	5.15	4.10

n.a. = not applicable
 n.d. = not detected

Table 3 Emulsion:
Theoretical solids content: STY/BA/MA-emulsions:46%
Reductant: SFS/Fe(II) Ox : SFS : Fe = 1 : 1 : 0.01

Initiator	Monomers	[Initiator] meq	Solids	Residual monomers STY BA	Mw	Mn	D	pH
$K_2S_2O_8$	STY/BA/MA	1.04	44.8	n.d.	1753000	346000	5.07	2.19
Tx C	STY/BA/MA	2.08	45.1	n.d.	690000	169000	4.1	2.0
	STY/BA/MA	1.04	48.3	0.04	713700	144300	4.95	4.20
Tx 22	STY/BA/MA	2.08	50.0	n.d.	529500	70900	7.47	1.92
Tx 117	STY/BA/MA	1.04	47.0	0.10	536080	140400	3.82	4.40
Laurox	STY/BA/MA	1.04	45.5	n.d.	2367400	426300	5.55	6.30

n.a. = not applicable

n.d. = not detected

Styrene/butyl acrylate/methacrylic acid : 4/6/0.1

Tx C = tert-butyl peroxybenzoate

Tx 22 = 1,1 di(tert-butylperoxy)cyclohexane

Tx 117 = tert-butylperoxy-2-ethylhexyl carbonate

Laurox = di-lauroyl peroxide

Results

As reference the emulsion copolymerization of vinylacetate and VeoVa with potassium persulfate at 70°C was used (thermal conditions).

5

The results show low residual monomer levels for the non-water-soluble organic peroxides (peroxyesters) under redox conditions. As the efficiency of the non-water-soluble peroxyesters such as Trigonox C was much higher than that of the water-soluble persulfates and hydroperoxides, the levels of addition
10 could be lowered to 20-40% of the original milli-equivalents of initiator used. Due to lower amounts of initiator and reductor, a higher value for pH and lower values for the conductivity were obtained. The prepared polymer had molecular weights (M_w/M_n) comparable with those of the reference copolymer of VeoVa/VAc.

15

The peroxyesters such as Trigonox 21 gave a high conversion of monomers at ambient temperature.

The invention is not limited to the above description; rather, the requested
20 rights are determined by the following claims.

CLAIMS

1. A process for emulsion polymerization comprising the steps of reacting together a polymerization initiator, a reductor, and a polymerizable species, with the proviso that the polymerization initiator is not a hydroperoxide, characterized in that the polymerization initiator and the reductor are reacted together to provide a free radical moiety of the initiator, whereupon this free radical moiety initiates polymerization of the polymerizable species, this step being carried out at an initial cold start temperature, whereafter the temperature is increased to follow a temperature profile to a final preselected polymerization temperature.
2. Process according to claim 1 carried out at an initial temperature of up to 70°C, for example carried out at an initial temperature of up to 50°C and preferably of up to 35°C.
3. Process according to claim 1 or 2 carried out at an initial temperature lying in the range of +10° to 35°C, preferably in the range of 15° to 25°C.
4. Process according to any one of the preceding claims wherein the initial temperature is maintained for a predetermined length of time, for example up to 2 hours, preferably up to 1 hour, most preferably up to half an hour.
5. Process according to any one of the preceding claims wherein the temperature is increased subsequent to the initial temperature maintenance period to follow a temperature profile to a final polymerization temperature, preferably up to a final polymerization temperature of at the most 90°C, and wherein the final polymerization temperature preferably lies in the range of 50-80°C and most preferably is

70°C or less.

- 5 6. Process according to claim 5 wherein the initial temperature is increased incrementally per pre-selected time period, preferably by about 20°C per hour.
- 10 7. Process according to claim 6 wherein the initiator is selected from the group consisting essentially of: diisobutanoyl peroxide, cumyl peroxyneodecanoate, 2,4,4-trimethylpentyl-2-peroxyneodecanoate, tert-amyl peroxyneodecanoate, bis(4-tert-butylcyclohexyl)peroxydicarbonate, bis(-ethylhexyl)peroxydicarbonate, tert-butyl peroxyneodecanoate, dibutyl peroxydicarbonate, dicetyl peroxydicarbonate, dimyristyl peroxydicarbonate, tert-amyl peroxy-pivalate, tert-butyl peroxy-pivalate, bis(3,5,5-trimethylhexanoyl) peroxide, dilauroyl peroxide, didecanoyl peroxide, 2,5"-
- 15 bis(2-ethylhexanoylperoxy)-2,5-dimethylhexane, tert-amyl peroxy-2-ethylhexanoate, dibenzoyl peroxide, tert-butyl peroxy-2-ethylhexanoate, tert-butyl peroxydiethylacetate, 1,4-bis(tert-butylperoxycarbo)cyclohexane, tert-butyl peroxyisobutanoate, 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, 1,1-bis(tert-butylperoxy)cyclohexane, tert-butyl
- 20 peroxy-3,5-trimethylhexanoate, 2,2-bis(tert-butylperoxy)butane, tert-butylperoxy isopropyl carbonate, tert-butylperoxy 2-ethylhexyl carbonate, tert-butyl peroxyacetate, tert-butyl peroxybenzoate, di-tert-amyl peroxide, dicumyl peroxide, bis(tert-butylperoxyisopropyl)benzene, 2,5-bis(tert-butylperoxy)-2,5-dimethylhexane, tert-butyl cumyl peroxide, 2,5-bis(tert-
- 25 butylperoxy)-2,5-dimethyl-3-hexyne, and di-tert-butyl peroxide.
8. Process according to claim 7 wherein the initiator is substantially non-water-soluble and is selected from the group consisting essentially of:
- alifatic and aromatic peroxyesters, preferably tert-butyl peroxy-2-

ethylhexanoate (Trigonox 21), tert-amyl peroxy-2-ethylhexanoate, tert-butyl peroxybenzoate (Trigonox C), tert-amyl peroxybenzoate, tert-butyl peroxyacetate, tert-butyl peroxy-3,5-trimethylhexanoate, tert-butyl peroxyisobutanoate, tert-butyl peroxydiethylacetate, tert-butyl peroxy-pivalate;

5 - peroxycarbonates, preferably tert-butyl peroxyisopropyl carbonate (Trigonox BPIC), and tert-butyl peroxy-2-ethyl hexyl carbonate Trigonox 117).

10 9. Process according to any one of the preceding claims wherein the reductor is chosen from the group consisting essentially of: sodium formaldehyde sulfoxylate (SFS), sodium bisulfite, Ascorbic acid (vitamin C), aldehydes, for example glutaraldehyde, sodium metabisulfite, sodium dithionate, and sugars.

15 10. Process according to any one of the preceding claims wherein the polymerizable species is selected from the group consisting essentially of: acrylonitrile, acrylic acid, methyl acrylate, ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, methoxyethyl acrylate, dimethyl aminoacrylate,

20 methacrylic acid, methyl methacrylate, ethyl methacrylate, butyl methacrylate, isobutyl methacrylate, 2-ethylhexyl methacrylate, lauryl methacrylate, stearic methacrylate, dimethyl aminomethacrylate, allyl methacrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, 2-hydroxyethyl methacrylate, 2-hydroxypropyl methacrylate, acrylamide,

25 methacrylamide, glycidyl acrylate, vinyl ester of versatic acid, styrene, para-methyl styrene, vinyl acetate, alpha-methyl styrene.

11. Process according to any one of the preceding claims carried out in the presence of a catalyst, said catalyst preferably being a water-soluble salt

derived from a transition metal, and most preferably being selected from the group consisting essentially of Fe^{2+} , Co^{3+} , Cu^+ , and Ce^{3+} .

- 5 12. Process according to any one of the preceding claims wherein the initiator and the reductor are provided in the following ratios 10:1 to 1:5, preferably 4:1 to 1:2.
- 10 13. Process according to any one of the preceding claims wherein the ratio of catalyst: oxidator is about 0-0.1 on a molar basis.
14. A polymer obtainable according to the process of any one of the preceding claims.
- 15 15. Polymer according to claim 14 having one or more of the following characteristics:
- a conductivity lower than about 5,
- a low residual monomer level,
- a particle size of less than about 220 nm, preferably less than 200 nm.
- 20 16. Use of a polymer according to claims 14 and/or 15 in coatings and/or adhesives.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/07769

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F4/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 022 281 A (E. S. SMITH) 20 February 1962 (1962-02-20) claim 1	1
A	GB 1 558 835 A (JAPAN SYNTHETIC RUBBER CO.) 9 January 1980 (1980-01-09)	

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

17 January 2000

Date of mailing of the international search report

24/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/07769

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3022281 A	20-02-1962	DE 1099738 B FR 1236360 A GB 851964 A	16-11-1960
GB 1558835 A	09-01-1980	JP 1298730 C JP 52084269 A JP 60023681 B JP 1298731 C JP 52084268 A JP 60023682 B JP 1250848 C JP 52084275 A JP 59013525 B US 4201848 A	31-01-1986 13-07-1977 08-06-1985 31-01-1986 13-07-1977 08-06-1985 14-02-1985 13-07-1977 30-03-1984 06-05-1980

THIS PAGE BLANK (USPTO)